



MITO 80 ohm

Indium Tin Oxide Coated Polyester

Our range of Indium Tin Oxide (ITO) Coated Polyester Film has been developed to meet the ever demanding needs of the market for a high quality transparent conductive film.

Our products have been utilised in a wide range of applications such as Electroluminescent (EL) Lamps, Touch Screens, Position Sensors, Transparent Heaters, Shielding and Liquid Crystal Displays (LCD).

The MITO series is produced utilising a vacuum sputtering process that ensures an excellent coating uniformity and adhesion to the base film.

High visible light transmission and low reflection are optimised for improved end product performance.

MITO features electrical uniformity of 10 ohms per square foot.

Our standard roll length is 100m in widths of 305mm and 610mm, custom widths and lengths are available on request.

PET Properties		MITO-80-125	MITO-80-175	Testing Method
Thickness (µm)		125	175	Micrometer
Light Transmission (%)		89.10	88.70	ASTM D 1003
Haze (%)		2.60	3.30	ASTM D 1003
Tensile Strength (Mpa)	MD	181	163	ASTM D 882
	TD	198	187	
Elongation @ Break (%)	MD	128	159	ASTM D 882
	TD	109	135	
Heat Shrinkage (%)	MD	0.56	0.43	ASTM D 1024 (150°C, 30 min)
	TD	0.38	0.33	

ITO Properties		MITO-80-125	MITO-80-175	Testing Method
PET Thickness (µm)		125	175	Micrometer
VLT (%)		78.80	78.80	ASTM D 1003
Haze (%)		2.50	2.50	ASTM D 1003
Clarity (%)		98	98	ASTM D 1003
Resistance Level (ohm/sq)		80	80	ASTM D 991
Uniformity (%)		15	15	ASTM D 991
Coating Adhesion (%)		100	100	ASTM D 3359
Shrinkage (%)		0.30	0.30	ASTM D 1024
		0.18	0.18	
Heat Test		20	20	30 min @ 110°C

Product Handling:

As with all vacuum deposited thin film, it is relatively easy to scratch or crack the coating if the ITO layer is not handled with care. Care should be taken when the film is unwound from the roll to ensure it is not bent or creased.

It is important never to allow the ITO coated side of the film to come into contact with a table or any such surfaces that could potentially scratch the coating which could lead to increased surface resistance and visible defects.

Before adopting our products for commercial use, the user assumes responsibility for determining fitness of use in their particular application and process.

Memcon makes no warranties and assumes no liability in connection with any use of this information.

MEMCON (Asia) Limited
 Units 5/6 6/F Westley Square
 48 Hoi Yuen Rd Kwun Tong Hong Kong
 T +852 3741 1411 F +852 3747 8980
 www.memcon.asia sales@memcon.asia

MEMCON Limited
 Unit 8 Campus Five Third Avenue LETCHWORTH
 Hertfordshire SG6 2JF United Kingdom
 T +44 1462 371477 F +44 1462 677499
 www.memcon.eu sales@memcon.eu

MEMCON North America
 6000 Red Arrow Hwy Unit 1
 Stevensville Michigan 49127 USA
 T +1 269 281 0478 F +1 269 593 5952
 www.memcon.net sales@memcon.net