



# MITO 100 ohm

## Indium Tin Oxide Coated Polyester

Our range of Indium Tin Oxide (ITO) Coated Polyester Film has been developed to meet the ever demanding needs of the market for a high quality transparent conductive film.

Our products have been utilised in a wide range of applications such as Electroluminescent (EL) Lamps, Touch Screens, Position Sensors, Transparent Heaters, Shielding and Liquid Crystal Displays (LCD).

The MITO series is produced utilising a vacuum sputtering process that ensures an excellent coating uniformity and adhesion to the base film.

High visible light transmission and low reflection are optimised for improved end product performance.

Standard roll length is 100M in widths of 305mm (R3) and 610mm (R4), custom widths such as 1000 or 1200mm are also available.

PET Properties		MITO-100-125	MITO-100-175	Testing Method
Thickness (µm)		125	175	Micrometer
Light Transmission (%)		89	89	ASTM D 1003
Haze (%)		2.3	2.4	ASTM D 1003
Tensile Strength (Mpa)	MD	177	181	ASTM D 882
	TD	214	198	
Elongation @ Break (%)	MD	130	180	ASTM D 882
	TD	110	120	
Heat Shrinkage (%)	MD	1.1	0.9	ASTM D 1024 30 min @ 150°C
	TD	0.2	0.0	

ITO Properties		MITO-100-125	MITO-100-175	Testing Method
PET Thickness (µm)		125	175	Micrometer
VLT (%)		78	78	ASTM D 1003
Haze (%)		< 3	< 3	ASTM D 1003
Surface Free Energy		≥ 30 J.m.2	≥ 30 J.m.2	ASTM D 1003
Resistance Level (ohm/sq)		90-110	90-110	ASTM D 991
Uniformity (%)		± 20	± 20	ASTM D 991
Coating Adhesion (%)		100	100	ASTM D 3359
Shrinkage (%)	MD	0.5	0.5	30 min @ 140°C
	TD	0.2	0.2	30 min @ 140°C

### Product Handling:

As with all vacuum deposited thin film, it is relatively easy to scratch or crack the coating if the ITO layer is not handled with care. Care should be taken when the film is unwound from the roll to ensure it is not bent or creased.

It is important never to allow the ITO coated side of the film to come into contact with a table or any such surfaces that could potentially scratch the coating which could lead to increased surface resistance and visible defects.

Before adopting our products for commercial use, the user assumes responsibility for determining fitness of use in their particular application and process.

Memcon makes no warranties and assumes no liability in connection with any use of this information.

**MEMCON (Asia) Limited**  
 Units 5/6 6/F Westley Square  
 48 Hoi Yuen Rd Kwun Tong Hong Kong  
 T +852 3741 1411 F +852 3747 8980  
 www.memcon.asia sales@memcon.asia

**MEMCON Limited**  
 Unit 8 Campus Five Third Avenue Letchworth  
 Hertfordshire SG6 2JF United Kingdom  
 T +44 1462 371477 F +44 1462 677499  
 www.memcon.eu sales@memcon.eu

**MEMCON North America**  
 4500 Red Arrow Hwy Unit E  
 Stevensville Michigan 49127 USA  
 T +1 269 281 0478 F +1 269 593 5952  
 www.memcon.net sales@memcon.net